



PHYSICAL PROPERTIES AVONITE® ACRYLIC SOLID SURFACING SHEETS 3MM

Aristech Surfaces' Avonite Acrylic Solid Surface "Specialty Blend Solid Surface" sheet products in a variety of attractive colors provide exceptionally weatherable, strong, non-porous, scratch and stain resistant material for architectural designs and utilitarian surfaces.

PROPERTY	UNITS	SOLIDS	PARTICULATE	TEST METHOD
General				
Nominal Thickness*	mm	3mm	3mm	-
Density	g/cm ³	1.73	1.60	ASTM D 792
Water Absorption	%	0.13	0.08	ASTM D 570
Mechanical				
Tensile Strength	MPa	33.4	27.6	ASTM D 638
Tensile Modulus	MPa	7,010	7,650	ASTM D 638
Tensile Elongation	%	1.40	1.50	ASTM D 638
Flexural Strength	MPa	71.0	55.2	ASTM D 790
Flexural Modulus	MPa	6,070	6,720	ASTM D 790
Barcol Hardness	-	59	57	ASTM D 2583
Rockwell Hardness (M Scale)	-	86	94	ASTM D 785
Charpy Impact	J/m	104.0	48.0	ASTM D 6110
Ball Impact (227g ball, no failure) Supported	cm	>380	>380	NEMA LD3-3.8
Ball Impact (227g ball, no failure) UnSupported	cm	213	152	NEMA LD3-3.8
Thermal				
DTUL @ 264 psi	°C	88	93	ASTM D 648
Coefficient of Thermal Expansion	cm/cm/ °C		4.43 x 10 ⁻⁵	ASTM D 696
Boiling Water Resistance	-	No Effect	No Effect	ISFA 2-01
High Temperature Resistance	-	No Effect	No Effect	ISFA 2-01
Reaction to Fire	-	Class B	Class B	ASTM E 84
Combustion Toxicity	-	98	67	Pittsburgh Protocol
Total volatile Organic Compounds	µg/m ² /hr	69.1	69.1	ASTM D 5116
Surface				
Consistency Of Color (Same Sheet)	-	Passes	Passes	ISFA 2-01
Light Resistance	-	No Effect	No Effect	ISFA 2-01
Cleanability/Stain Resistance	-	Passes	Passes	NEMA LD3-3.4
Stain Resistance	-	Passes	Passes	ANZI/ICPA SS-1
Bacterial Resistance	-	No growth	No growth	ASTM G 22
Fungi Resistance	-	No growth	No growth	ASTM G 21
Food Zone Use	-	Approved	Approved	NSF 51





Note: for cautions and information on exposure to any Aristech Surfaces' product, please see the applicable material safety data sheet.

Information contained herein is: a) based on Aristech Surfaces' available technical data and experience; b) intended only for individuals having applicable technical skill, with such individuals assuming full responsibility for all design, fabrication, installation, and hazards; c) to be used with discretion and at one's own risk, after consultation with local codes and with one's independent determination that the product is suitable for the intended use; and d) not to be used to create designs, specifications, or installation guidelines. **Aristech Surfaces makes no representation, or warranty, express or implied, and assumes no liability or responsibility as to:** i) the accuracy, completeness or applicability of any supplied information; ii) results obtained from use of the information, whether or not resulting from Aristech Surfaces' negligence; iii) title, and/or non-infringement of third party intellectual property rights; iv) the merchantability, fitness or suitability of the product for any purpose; or v) health or safety hazards resulting from exposure to or use of the product. **Aristech Surfaces shall not be liable for** x) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and y) special, direct, indirect or consequential damages.

