

## Physical Properties – STUDIO Collection®

Aristech Surfaces' STUDIO Collection "Specialty Blend" polyester sheet products in a variety of attractive colors and patterns provide strong, non-porous, scratch and stain resistant material for architectural designs.

PROPERTIES	UNITS	GLASS / TRANSLUCENT	RECYCLED / NON- TRANSLUCENT	TEST METHOD
<b>GENERAL</b>				
Nominal Thickness	mm	12mm	12mm	-
Density	g/cm <sup>3</sup>	1.30	1.60	ASTM D 792
Water Absorption	%	0.04	0.05	ASTM D 570
<b>MECHANICAL</b>				
Tensile Strength	MPa	15.9	22.8	ASTM D 638
Tensile Modulus	MPa	4,550	7,165	ASTM D 638
Tensile Elongation	%	0.34	0.65	ASTM D 638
Flexural Strength	MPa	28.3	38.4	ASTM D 790
Flexural Modulus	MPa	4,515	6,730	ASTM D 790
Barcol Hardness	-	48	53	ASTM D 2583
Rockwell Hardness (M Scale)	-	104	98	ASTM D 785
Charpy Impact	J/m	26.7	37.4	ASTM D 6110
Ball Impact (½ lb. ball, no failure) Supported	cm	>380	>380	NEMA LD3-3.8
Ball Impact (½ lb. ball, no failure) Unsupported	cm	138	244	NEMA LD3-3.8
<b>THERMAL</b>				
DTUL @ 264 psi	°C	72	77	ASTM D 648
Coefficient of Thermal Expansion	cm/cm/°C	5.2x10 <sup>-5</sup>	3.8x10 <sup>-5</sup>	ASTM D 696
Boiling Water Resistance	-	No Effect	No Effect	ISFA 2-01
High Temperature Resistance	-	No Effect	No Effect	ISFA 2-01
Flame Spread Index	-	180	20	ASTM E 84
Smoke Generation Index	-	>450	155	ASTM E 84
Combustion Toxicity	-	19.3	62.3	Pittsburgh Protocol
Total volatile Organic Compounds	µg/m <sup>2</sup> /hr	13.9	3.90	OASTM D 5116
<b>SURFACE</b>				
Consistency Of Color (Same Sheet)	-	Passes	Passes	ISFA 2-01
Light Resistance	-	No Effect	No Effect	ISFA 2-01
Cleanability/Stain Resistance	-	Passes	Passes	NEMA LD3-3.4
Stain Resistance	-	Passes	Passes	ANZI/ICPA SS-1
Bacterial Resistance	-	No growth	No growth	ASTM G 22
Fungi Resistance	-	No growth	No growth	ASTM G 21



Food Zone Use	-	Approved	Approved	NSF 51
---------------	---	----------	----------	--------

**NOTE: FOR CAUTIONS AND INFORMATION ON EXPOSURE TO ANY ARISTECH SURFACES' PRODUCT, PLEASE SEE THE APPLICABLE MATERIAL SAFETY DATA SHEET.**

Information contained herein is: a) based on Aristech Surfaces'available technical data and experience; b) intended only for individuals having applicable technical skill, with such individuals assuming full responsibility for all design, fabrication, installation, and hazards; c)to be used with discretion and at one's own risk, after consultation with local codes and with one's independent determination that the product is suitable for the intended use; and d)not to be used to create designs, specifications, or installation guidelines. **Aristech Surfaces makes no representation, or warranty, express or implied, and assumes no liability or responsibility as to:** i) the accuracy, completeness or applicability of any supplied information; ii) results obtained from use of the information, whether or not resulting from Aristech Surfaces' negligence; iii) title, and/or non-infringement of third party intellectual property rights; iv) the merchantability, fitness or suitability of the product for any purpose; or v) health or safety hazards resulting from exposure to or use of the product. **Aristech Surfaces shall not be liable for** x) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and y) special, direct, indirect or consequential damages.

