

Physical Properties – 3.2mm

Aristech Surfaces has offered a full line of premium materials for use in manufacturing bathtubs, wash basins, shower walls/trays, sinks/bowls and more. As a pioneer in material innovations, Aristech Surfaces LLC has recently unveiled a leading-edge designer surface material known simply as AVONITE® Flex. Application can range from hot tub, bath, sanitaryware and architectural applications, to specialty market applications and more.

AVONITE® Flex is an innovative material formulation infused within the full depth of this

designer surface, offering the ability to pull and thermoform to tight detail, while maintaining the premium matte finish even within deep draws. A premiere collection for OEM's, fabricator, and designers, of premium continuous cast specialty materials promoting lightweight handling, hygienic non-porous surface properties, manufactured with a luxurious matte aesthetic and offered in a boutique collection of white hues. The latest sought-after aesthetics in the most malleable of forms.

For over 50 years, Aristech Surfaces LLC has produced and marketed a broad range of surface and design materials for bath, shower, architectural applications to provide quality, cost-conscious and high-end aesthetic solutions sought by OEMs, architects, designers and fabricators for industries around the globe.

Property	Units	3.2mm	Test Method
General:			
Nominal Thickness	inches	0.125	—
Density	g/cm ³	1.30	ASTM D 792
Water Absorption	%	0.19	ASTM D 570
Mechanical:			
Tensile Strength	psi	7,590	ASTM D 638
Tensile Modulus	psi	594,000	ASTM D 638
Tensile Elongation	%	1.60	ASTM D 638
Flexural Strength	psi	13,320	ASTM D 790
Flexural Modulus	psi	533,000	ASTM D 790
Barcol Hardness	—	53	ASTM D 2583
Rockwell Hardness (M Scale)	—	99	ASTM D 785
Charpy Impact	ft-lbs/in.	1.98	ASTM D 6110
Ball Impact (½ lb. ball, no failure)	inches	>150	NEMA LD3-3.8
Supported			
Ball Impact (½ lb. ball, no failure) Unsupported	inches	36	NEMA LD3-3.8
Thermal:			
DTUL @ 264 psi	°F	190	ASTM D 648
Coefficient of Thermal Expansion	in/in/°F	3.26x10 ⁻⁵	ASTM D 696
Surface:			
Consistency of Color (Same Sheet)	—	Passes	ISFA 2-01
Light Resistance	—	No Effect	ISFA 2-01
Cleanability/Stain Resistance	—	Passes	NEMA LD3-3.4
Stain Resistance	—	Passes	ANSI/ICPA SS-1
Food Zone Use	—	Approved	NSF 51

Note: For cautions and information on exposure to any Aristech Surfaces LLC product, please see the applicable material safety data sheet (SDS).

Information contained herein is: a) based on Aristech Surfaces' available technical data and experience; b) intended only for individuals having applicable technical skill, with such individuals assuming full responsibility for all design, fabrication, installation, and hazards; c) to be used with discretion and at one's own risk, after consultation with local codes and with one's independent determination that the product is suitable for the intended use; and d) not to be used to create designs, specifications, or installation guidelines. **Aristech Surfaces makes no representation, or warranty, express or implied, and assumes no liability or responsibility as to:** i) the accuracy, completeness or applicability of any supplied information; ii) results obtained from use of the information, whether or not resulting from Aristech Surfaces' negligence; iii) title, and/or non-infringement of third party intellectual property rights; iv) the merchantability, fitness or suitability of the product for any purpose; or v) health or safety hazards resulting from exposure to or use of the product. **Aristech Surfaces shall not be liable for** x) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and y) special, direct, indirect, or consequential damages.

