



PHYSICAL PROPERTIES AVONITE® ACRYLIC SOLID SURFACING SHEETS 6MM

Aristech Surfaces' Avonite Acrylic Solid Surface "Specialty Blend Solid Surface" sheet products in a variety of attractive colors provide exceptionally weatherable, strong, non-porous, scratch and stain resistant material for architectural designs and utilitarian surfaces.

PROPERTY	UNITS	SOLIDS	SMALL PARTICULATE	MEDIUM PARTICULATE	LARGE PARTICULATE	TEST METHOD
General						
Nominal Thickness	mm	6mm	6mm	6mm	6mm	-
Density	g/cm ³	1.73	1.60	1.62	1.63	ASTM D 792
Water Absorption	%	0.04	0.05	0.05	0.05	ASTM D 570
Mechanical						
Tensile Strength	psi	4,500	4,500	4,100	3,650	ASTM D 638
Tensile Modulus	psi	1,525,000	1,036,000	1,220,000	1,190,000	ASTM D 638
Tensile Elongation	%	0.40	1.00	0.55	0.45	ASTM D 638
Flexural Strength	psi	9,300	8,000	7,150	6,850	ASTM D 790
Flexural Modulus	psi	1,260,000	1,063,000	1,050,000	1,170,000	ASTM D 790
Barcol Hardness	-	63	58	59	60	ASTM D 2583
Rockwell Hardness (M Scale)	-	94	94	93	93	ASTM D 785
Charpy Impact	ft-lbs/inch	1.10	1.10	0.85	0.80	ASTM D 6110
Ball Impact (½ lb. ball, no failure)	Inches	>150	>150	>150	>150	NEMA LD3-3.8
Supported						
Ball Impact (½ lb. ball, no failure)	Inches	84	60	60	42	NEMA LD3-3.8
Unsupported						
Thermal						
DTUL @ 264 psi	°F	215	200	200	198	ASTM D 648
Coefficient of Thermal Expansion	in/in/°F	2.09x10 ⁻⁵	2.46x10 ⁻⁵	2.46x10 ⁻⁵	2.46x10 ⁻⁵	ASTM D 696
Boiling Water Resistance	-	No Effect	No Effect	No Effect	No Effect	ISFA 2-01
High Temperature Resistance	-	No Effect	No Effect	No Effect	No Effect	ISFA 2-01
Reaction to Fire	-	Class A	Class B	Class B	Class B	ASTM E 84
Combustion Toxicity	-	98	67	67	67	Pittsburgh Protocol
Total Volatile Organic Compounds	µg/m ² /hr	69.1	69.1	69.1	69.1	ASTM D 5116
Surface						
Consistency Of Color	-	Passes	Passes	Passes	Passes	ISFA 2-01



PROPERTY	UNITS	SOLIDS	SMALL PARTICULATE	MEDIUM PARTICULATE	LARGE PARTICULATE	TEST METHOD
(Same Sheet)						
Light Resistance	-	No Effect	No Effect	No Effect	No Effect	ISFA 2-01
Cleanability/Stain Resistance	-	Passes	Passes	Passes	Passes	NEMA LD3-3.4
Stain Resistance	-	Passes	Passes	Passes	Passes	ANZI/ICPA SS-1
Bacterial Resistance	-	No growth	No growth	No growth	No growth	ASTM G 22
Fungi Resistance	-	No growth	No growth	No growth	No growth	ASTM G 21
Food Zone Use	-	Approved	Approved	Approved	Approved	NSF 51

Note: for cautions and information on exposure to any Aristech Surfaces' product, please see the applicable material safety data sheet.

Information contained herein is: a) based on Aristech Surfaces' available technical data and experience; b) intended only for individuals having applicable technical skill, with such individuals assuming full responsibility for all design, fabrication, installation, and hazards; c) to be used with discretion and at one's own risk, after consultation with local codes and with one's independent determination that the product is suitable for the intended use; and d) not to be used to create designs, specifications, or installation guidelines. **Aristech Surfaces makes no representation, or warranty, express or implied, and assumes no liability or responsibility as to:** i) the accuracy, completeness or applicability of any supplied information; ii) results obtained from use of the information, whether or not resulting from Aristech Surfaces' negligence; iii) title, and/or non-infringement of third party intellectual property rights; iv) the merchantability, fitness or suitability of the product for any purpose; or v) health or safety hazards resulting from exposure to or use of the product. **Aristech Surfaces shall not be liable for** x) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and y) special, direct, indirect or consequential damages.