

Physical Properties – AcrySan™

Aristech Acrylics AcrySan™ is a partially "cross-linked" commercial continuous cast acrylic sheet with unparalleled thermoforming properties. AcrySan™ was developed for plumbingware, spa, automotive and other applications.

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
General			
Thickness	0.125 (3.17)	Inch (mm)	—
Specific Gravity	1.19	—	ASTM D-792
Optical Unaged			
Refractive Index	1.49	—	ASTM D-542
Light Transmission	93.0	%	ASTM D-1003
Haze	0.8	%	ASTM D-1003
Ultraviolet Light Transmission (250-370 nanometers)	<1.0	%	UV Spectrophotometer
Optical aged			
Light Transmission	93.0	%	ASTM D-1003
Haze	1.0	%	ASTM D-1003
Yellowness Index	+ 0.45	YI	ASTM D-1925
Mechanical			
Tensile Strength	10,000 (68.9)	psi (MPa)	ASTM D-638
Tensile Modulus	460,000 (3,171)	psi (MPa)	ASTM D-638
Tensile Elongation	5.5	%	ASTM D-638
Flexural Strength	15,500 (106)	psi (MPa)	ASTM D-790
Flexural Modulus	450,000 (3,102)	psi (MPa)	ASTM D-790
Notched Izod Impact	0.4 (2.1)	ft-lb/in. of notch (kJ/m ²)	ASTM D-256 (Method A)
Charpy Impact (Un-notched)	4.6 (24.2)	ft.-lb./in. (kJ/m ²)	ASTM D-6110
Falling Dart Impact	3.0 (4.1)	ft.-lbs. (J)	FTMS 406-M-1074
Rockwell Hardness (M)	90 - 100	—	ASTM D-785
Barcol Hardness	48 - 52	—	ASTM D-2583

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Thermal			
DTUL @ 264 psi (1.82 MPa)	190 (88)	°F (°C)	ASTM D-648
Thermal Conductivity	1.4 (20.2)	Btu/(h·ft²·°F/in) (W/(m²·K/cm))	Cinco-Fitch
Specific Heat	0.35 (1465)	Btu/(lb·°F) (J/(kg·K))	ASTM C-351
Coefficient of Linear Thermal Expansion	4.1 x 10 ⁻⁵ (7.4 x 10 ⁻⁵)	in./in./°F (cm/cm/°C)	ASTM D-696
Thermal Stability 30 min.@ 356°F(180°C)	No degradation	—	ASTM D-4802
Flammability	94 HB	—	UL Test # 94
Miscellaneous			
Water Absorption	0.33	%	ASTM D-570

Note: for cautions and information on exposure to any Aristech Surfaces' product, please see the applicable material safety data sheet.

Information contained herein is: a) based on Aristech Surfaces' available technical data and experience; b) intended only for individuals having applicable technical skill, with such individuals assuming full responsibility for all design, fabrication, installation, and hazards; c) to be used with discretion and at one's own risk, after consultation with local codes and with one's independent determination that the product is suitable for the intended use; and d) not to be used to create designs, specifications, or installation guidelines. **Aristech Surfaces makes no representation, or warranty, express or implied, and assumes no liability or responsibility as to:** i) the accuracy, completeness or applicability of any supplied information; ii) results obtained from use of the information, whether or not resulting from Aristech Surfaces' negligence; iii) title, and/or non-infringement of third party intellectual property rights; iv) the merchantability, fitness or suitability of the product for any purpose; or v) health or safety hazards resulting from exposure to or use of the product. **Aristech Surfaces shall not be liable for** x) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and y) special, direct, indirect or consequential damages.

