

Typical properties of M-CYCLOSE® recycling plastic compounds

	Unit	M-CYCLOSE® rPE 068 UBQ10 nat	M-CYCLOSE® rPE 055 UBQ20 nat	M-CYCLOSE® rPE 044 UBQ30 nat	M-CYCLOSE® PPH 280 UBQ30 nat
Appearance	-	grey	dark grey	dark grey	dark brown
Recycled content	%	>98	>98	>98	30
Source	-	PCR	PCR	PCR	PCR
Density	g/cm ³	0.97	0.99	1.03	0.99
MFR (190 °C/2.16 kg)	g/10 min	6.8	5.5	4.4	28 ^d
Tensile modulus ^b	MPa	950	1,150	1,200	1,800
Tensile strength at yield ^b	MPa	20	19	17	23
Elongation at yield ^b	%	10	9	8	5
Elongation at break ^b	%	11	10	9	12
Charpy notched impact strength +23 °C ^c	kJ/m ²	57	38	25	19
Charpy unnotched impact strength +23 °C ^c	kJ/m ²	3.5	4.1	4.0	2.1
Suitable for	-	Injection moulding (Consumer goods, boxes, technical parts etc.)	Injection moulding (Consumer goods, boxes, technical parts etc.)	Injection moulding (Consumer goods, boxes, technical parts etc.)	Injection moulding (Consumer goods, boxes, technical parts etc.)

^a The allocation factor is the percentage of biomass allocated to the product (max. value: 100%) = percentage of replaced fossil based resources in the value chain. The allocation factor does not indicate how much biomass is actually in the product. It refers to the organic content (e.g. polymers) in the product. ^b ISO 527-1/-2 ^c ISO 179-1/1eA ^d MFR (230°C/2.16 kg)

The information given here is only valid for M-CYCLOSE® grades in their original packaging, sold by BIO-FED® and/or its authorized partners. If M-CYCLOSE® grades are mixed in any capacity with foreign material, beside masterbatches recommended by BIO-FED®, BIO-FED® declines any further responsibility. M-CYCLOSE® grades shall be stored in dry, closed rooms in closed packaging in original state. For keeping the product properties, the material must be protected against direct sun and the temperature must not exceed 50 °C at any time during transport and storage. M-CYCLOSE® grades have a remaining shelf life of twelve (12) months at room temperature (23 °C) from the delivery date. We recommend that products made of M-CYCLOSE® grades shall be stored under same conditions. All M-CYCLOSE® products listed here can be colored with AF-Color® and AF-Carbon® masterbatches from AF-COLOR. Furthermore AF-Complex® additive masterbatches are available. Please note that the use of masterbatches might influence the mechanical and/or optical properties of the final part.



BIO-FED

Member of the Feddersen Group

BioCampus Cologne · Nattermannallee 1
50829 Cologne · Germany
Phone: +49 221 888894-00
Fax: +49 221 888894-99
info@bio-fed.com · www.bio-fed.com

The information contained herein is based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information supplied here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case. BIO-FED®, M-VERA®, M-BIOBASE®, M-CYCLOSE®, AF-Eco®, AF-Color®, AF-Carbon® and AF-Complex® are registered brands of AKRO-PLASTIC GmbH.

09/2025

