

Fatigue assessment – Akulon K224-G6 (PA6) at 8°C

| Parameter | Value / Assumption |
|--|---|
| Material | Akulon K224-G6 (PA6) |
| Temperature | 8°C |
| Humidity | 50% RH |
| Load | 25 kg (~245 N) |
| Area | 2 cm ² |
| Calculated stress | ~1.2 MPa |
| Fatigue level (10 ⁶ cycles) | ~100–115 MPa (temperature-dependent) |
| Fatigue safety margin | >80 times lower stress |
| Service life | Up to ~10 ⁶ cycles (depending on use) |
| Creep | Reduced at lower temperatures |
| Environmental impact | Moisture absorption reduced at lower temperatures |

Conclusion: At 8°C, the safety margin for fatigue is further improved compared to 23°C. The stress level remains very low relative to the material's fatigue properties, and there is assessed to be no risk of fatigue failure over a 100-year period under the given conditions.

Service life assessment – Akulon (PA6) at 23°C

Input data

Material: Akulon K224-G6 (PA6)

Temperature: 23°C

Humidity: 50% RH

Load: 25 kg

Area: 2 cm²

Calculated stress

Force: 245 N

Stress: approx. 1.2 MPa

Fatigue assessment

At 10⁶ cycles: approx. 100 MPa

Current stress: 1.2 MPa

→ >80 times lower than critical level

Service life (100 years)

Up to ~10⁶ cycles depending on use

→ No fatigue risk

Environmental impact

50% RH improves fatigue properties

Conclusion

No risk of fatigue failure over 100 years.

The design has a high safety margin.

Recommendation

Assess creep, temperature and local stresses.

Fatigue curve (reference)

Fatigue life time of Akulon K224-G6 at 23°C

