

Jali<sup>®</sup>, Scintilla<sup>®</sup>, Lumina<sup>™</sup>, SLANT<sup>®</sup>, Vapor<sup>™</sup>, Spark<sup>™</sup>, Celeste<sup>™</sup>, Ripple<sup>™</sup>, Infinity<sup>™</sup>

		Test			
		<b>ASTM E-84</b> Surface Burning Characteristics of Building Materials  Flame Spread Index: 0-25 (Class A) 26-75 (Class B) 76-200 (Class C) Smoke Developed Index: 450 Maximum	<b>UL 94</b> Flammability of Plastic Materials for Parts in Devices and Appliances	<b>ASTM D-1929</b> Determining Ignition Temperature of Plastics	<b>ASTM D-635</b> Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position
Panel Construction Type	Acrylic Clad Panels	<b>Class C</b> Flame Spread Index: 120	94 HB	Pass 850°	CC2
	Polycarbonate Clad Panels	<b>Class B</b> Flame Spread Index: 40	VO	Pass 1000°	CC1
	Glass Clad Panels	<b>Class A</b> Flame Spread Index: <25	Not applicable	Not applicable	Not applicable

\*Consistent with standard industry and testing practice, the flame spread and smoke developed were recorded while the material remained in the original test position and do not include the material that ignited on the furnace floor.

